



Early Journal Content on JSTOR, Free to Anyone in the World

This article is one of nearly 500,000 scholarly works digitized and made freely available to everyone in the world by JSTOR.

Known as the Early Journal Content, this set of works include research articles, news, letters, and other writings published in more than 200 of the oldest leading academic journals. The works date from the mid-seventeenth to the early twentieth centuries.

We encourage people to read and share the Early Journal Content openly and to tell others that this resource exists. People may post this content online or redistribute in any way for non-commercial purposes.

Read more about Early Journal Content at <http://about.jstor.org/participate-jstor/individuals/early-journal-content>.

JSTOR is a digital library of academic journals, books, and primary source objects. JSTOR helps people discover, use, and build upon a wide range of content through a powerful research and teaching platform, and preserves this content for future generations. JSTOR is part of ITHAKA, a not-for-profit organization that also includes Ithaka S+R and Portico. For more information about JSTOR, please contact support@jstor.org.

VI. *An Account of some Experiments tried with Monsr. Villette's Burning Concave, in June 1718. By the Rev. Dr. J. Harris and Dr. J. T. Desaguliers, Reg. Soc. SS.*

THIS Miroir is a Concave 47 Inches wide, and ground to a Sphere of 76 Inches *Radius*; so that its *Focus* is about 38 Inches distant from the *Vertex* of the Glafs. The Metal of which it is made is a Mixture of Copper, Tin and Tin-Glafs, whose Reflexion has something of a yellow Cast. The Concave-Surface has scarce any Flaws, and those very small; but the Convex side, which is also polish'd, has some Holes in it.

Having held several Bodies in the *Focus* of this Miroir, we observ'd what happen'd to them whilst expos'd to this great Heat; and with an half second Pendulum took notice of the Time in which any material Change happen'd to them.

The Experiments were as follow, and made from Nine till Twelve in the Morning.

- N^o 1. A red piece of a *Roman Patra*, which began to melt in 3 Seconds, was ready to drop in 100.
 2. Another black Piece melted at 4, and was ready to drop at 64 Seconds.
 3. Chalk taken out of an *Echinus Spatagus* fill'd with Chalk only, fled away in 23 Seconds.
 4. A Fossile-Shell calcin'd in 7 Seconds, and did no more in 64.
 5. A piece of *Pompey's Pillar* at *Alexandria*, was vitrified in the Black Part in 50 Seconds, and in the White part in 54. 6. Cop-

6. Copper-Oar, that had no Metal in it visible, vitrified in 8 Seconds.

7. Slag, or Cinder of the ancient Iron-work said to have been wrought by the *Saxons*, ready to run in 29 Seconds and an half.

Here the Glass growing hot, burn'd with much less Force.

8. Iron-Oar fied at first, but melted in 24 Seconds.

9. Talk began to calcine at 40 Seconds, and held in the *Focus* 64.

10. *Calculus humanus* in 2 Seconds was calcin'd, and only dropp'd off in 60.

11. An anonymous Fish's Tooth melted in 32 Seconds and an half.

12. The *Asbestos* seem'd condens'd a little in 28 Seconds; but it was now something cloudy: *Monf. Villette* says that the Glass usually calcines it.

13. A Golden Marchasite broke to pieces, and began to melt in about 30 Seconds.

14. A Silver Sixpence melted in 7 Seconds and an half.

15. A King *William's* Copper Halfpeny melted in 20 Seconds, and ran with an Hole in it in 31.

16. A King *George's* Halfpenny melted in 16 Seconds, and ran in 34.

17. Tin melted in 3 Seconds.

18. Cast Iron in 16 Seconds.

19. Slate melted in 3 Seconds, had an Hole in 6.

20. Thin Tile melted in 4 Seconds, had a Hole and was vitrifi'd thro' in 80.

21. Bone calcin'd in 4 Seconds, and vitrifi'd in 33. An Emerald was melted into a Substance like a Turquois Stone.

A Diamond weighing 4 Grains lost $\frac{2}{3}$ of its Weight. VII. *Ab*